Q Bridge Thermal Conductor





GENERAL DESCRIPTION

A\/X's new Q-Bridge Thermal Conductor is manufactured with the highest quality materials for reliable and repeatable performance providing a cost effective thermal management solution. These devices are constructed with Aluminum Nitride (AIN) or Beryllium Oxide (BeO) and are available in standard EIA form factors.

Q-Bridge provides the designer with the ability to manage thermal conditions by directing heat to a thermal ground plane, heat sink or any other specific thermal point of interest. The inherently low capacitance makes this device virtually transparent at RF/microwave frequencies. This device has the added benefit of offering additional layers of protection to adjacent components from hot spot thermal loads.

Q-Bridge provides the benefit of increased overall circuit reliability. A\/X's Q-Bridge is manufactured using onepiece construction, providing a RoHS compliant SMT package that is fully compatible with high speed automated pick-andplace processing. It is available in 0302, 0402, 0603 and 0805 EIA case sizes. Custom configurations are also available

APPLICATIONS

- · High Thermal Conductivity
- · Low Thermal Resistance
- Low Capacitance
- · Increases Circuit Reliability
- · RoHS Compliant
- More efficient thermal management


FEATURES

- · GaN Power Amplifiers
- · High RF Power Amplifiers
- Filters
- Synthesizers
- · Industrial Computers
- Switch Mode Power Supplies
- · Pin & Laser Diodes

FUNCTIONAL APPLICATIONS

- · Between active device and adjacent ground planes
- · Specific contact pad to case
- · Contact pad to contact pad
- · Direct component contact to via pad or trace
- · Edges fully metalized

HOW TO ORDER





B = BeO





Style W = Edge Wrap E = No Wrap



Termination

Y = Silver Platinum, non-magnetic Termination

S = Silver over Magnetic Termination


L = 60Sn/40Pb solder plating Consult factory for other termination options e.g., tin plate and solder plate





Packaging
T = 1000pcs., 7" reel
T\500 = 500pcs., 7" reel
C = Matrix Tray

Size	Length	Width	Standard Thickness (T, mils)		Termination	
(EIA)	(L)	(W)	T1	T2	(1)	
0302	0.77 ± 0.051 (0.030 ± 0.002)	0.51 ± 0.051 (0.020 ± 0.002)	20	15	0.25 ± 0.051 (0.010 ± 0.002)	
0402	1.02 ± 0.051 (0.040 ± 0.002)	0.51 ± 0.051 (0.020 ± 0.002)	20	15	0.25 ± 0.051 (0.010 ± 0.002)	
0603	0.52 ± 0.051 (0.060 ± 0.002)	0.76 ± 0.051 (0.030 ± 0.002)	25	20	0.38 ± 0.051 (0.015 ± 0.002)	
0805	2.03 ± 0.051 (0.080 ±.002)	1.27 ± 0.051 (0.050 ± 0.002)	40	25	0.51 ± 0.051 (0.020 ± 0.002)	



AIN	Thermal Resistance (°C/W)		Thermal Condu	ctivity (mW/°C)	Capacitance Value (pF)*	
Case Size	Thickness T1	Thickness T2	Thickness T1	Thickness T2	Thickness T1	Thickness T2
0302	19	24	53	41	0.08	0.07
0402	25	32	40	30	0.06	0.05
0603	20	25	50	40	0.08	0.06
0805	10	16	100	60	0.13	0.08

BeO	Thermal Resistance (°C/W)		Thermal Conductivity (mW/°C)		Capacitance Value (pF)*	
Case Size	Thickness T1	Thickness T2	Thickness T1	Thickness T2	Thickness T1	Thickness T2
0302	12	15	81	63	0.07	0.06
0402	16	21	61	46	0.05	0.04
0603	13	16	76	61	0.06	0.05
0805	7	11	153	92	0.10	0.07

10